2009/22

ORACAL 651 **Intermediate Cal**

page 1 of 2

Description

Special PVC film with glossy or matt surface.

Release paper

Silicone coated paper on one side, 137 g/m², which provides excellent waste-stripping properties. For white vinyl a light blue silicone paper is used to form a stronger contrast to lettering.

Solvent polyacrylate, permanent

Area of use

Very good suitable for the use on cutting plotter systems. For short- and medium-term outdoor markings, letterings and decorations. Indoor exposure is almost unlimited. Glossy surface is additionally suitable for thermal transfer printing (with resin ribbons).

German General Type Approval (ABG, D5292) acc. to § 22a StVZO (Federal German Road Traffic Licensing Order);

B1-classification according to DIN 4102-1: Only flame resistant (class DIN 4102-B1) on steel planes.

Technical data

Thickness* (without protective paper and adhesive)	70 micron
Dimensional stability (FINAT TM 14)	adhered to steel, no measurable shrinkage in cross direction, in length 0.4 mm max.
Temperature resistance***	adhered to aluminium, -40°C to +80°C, no variation
Seawater resistance (DIN 50021)	adhered to aluminium, after 100h/23°C no variation
Adhesive power*	18 N/25 mm
(FINAT TM 1, after 24h, stainless steel)	
Tensile strength (DIN EN ISO 527)	
along	min. 19 MPa
across	min. 19 MPa
Elongation at break (DIN EN ISO 527)	
along	min. 130%
across	min. 150%
Shelf life**	2 years
Application temperature	>+8°C
Service life by specialist application	black / white: 5 years
under vertical outdoor exposure (normal climate of	transparent / coloured / metallic: 4 years
Central Europe)	brilliant blue: 3 years
* average ** in original packaging, at 20°C and 50% relative humidity *** normal climate of Central Europe	

^{*} average

The statements in this information sheet are based upon our knowledge and practical experience. This data is intended only as a source of information and is given without guarantee and does not constitute a warranty. Due to the wide variety of possible uses and applications customers should independently determine the suitability of this material for their specific purpose, prior to use.



Technical Data Sheet

ORACAL
651 Intermediate Cal

2009/22

page 2 of 2

Attention:

Surfaces to which the material will be applied must be thoroughly cleaned from dust, grease or any contamination which could affect the adhesion of the material. Freshly lacquered or painted surfaces should be allowed to dry for at least three weeks and to completely cure respectively. The compatibility of selected lacquers and paints should be tested by the user, prior to application of the material. Furthermore the application information published by ORAFOL is to be considered. The batch traceability according to ISO 9001 is possible on the basis of the roll number.

The statements in this information sheet are based upon our knowledge and practical experience. This data is intended only as a source of information and is given without guarantee and does not constitute a warranty. Due to the wide variety of possible uses and applications customers should independently determine the suitability of this material for their specific purpose, prior to use.

